

J-LASF015

$n_d = 1.804000$

$n_e = 1.808106$

$v_d = 46.60$

$v_e = 46.35$

Glass code (d)
804466
Glass code (e)
808464

Spectral l.	Refractive idx
2.058	1.76695
1.970	1.76858
1.530	1.77612
1.129	1.78310
1.064	1.78442
t	1.78553
s	1.78994
A'	1.793033
r	1.795917
C	1.798824
C'	1.799643
He-Ne	1.800408
D	1.803847
d	1.804000
e	1.808106
F	1.816078
F'	1.817079
g	1.825697
h	1.833795
0.389	1.838784
i	1.847835

Partial dispersion	
F-C	0.017254
F'-C'	0.017436
C-t	0.013293
C-A'	0.005791
d-C	0.005176
e-C	0.009282
g-d	0.021697
g-F	0.009619
h-g	0.008098
i-g	0.022138
C'-t	0.014112
e-C'	0.008463
F'-e	0.008973
i-F'	0.030756

Internal CC (80%/5%)	
355/312	
Color Code (80%/5%)	
385/315	
CCI	
B	0.00
G	0.53
R	0.54

Internal trans. (10mm)	
λ [nm]	τ
280	-
290	-
300	-
310	0.03
320	0.16
330	0.39
340	0.60
350	0.75
360	0.85
370	0.907
380	0.942
390	0.962
400	0.975
420	0.985
440	0.989
460	0.992
480	0.995
500	0.996
550	0.998
600	0.998
650	0.998
700	0.999
800	0.997
900	0.995
1000	0.996
1200	0.998
1400	0.997
1600	0.993
1800	0.986
2000	0.969
2200	0.923
2400	0.74

Thermal properties	
CTE(-30,70) [1E-7/°C]	60
CTE(100,300) [1E-7/°C]	75
Tg [°C]	697
At [°C]	728
StP [°C]	653
AP [°C]	683
SP [°C]	785
Ht condct. [W/m·K]	0.834
Sp. heat [kJ/kg·K]	0.470
Ht diffus. [1E-6 m2/sec]	0.387

Relative partial dispersion	
C-t/F-C	0.7704
C-A'/F-C	0.3356
d-C/F-C	0.3000
e-C/F-C	0.5380
g-d/F-C	1.2575
g-F/F-C	0.5575
h-g/F-C	0.4693
i-g/F-C	1.2831
C'-t/F'-C'	0.8094
e-C'/F'-C'	0.4854
F'-e/F'-C'	0.5146
i-F'/F'-C'	1.7639

Chemical properties [class]	
Acid res. (surface)	1
Alkaline detergent res.	1
Climate resistance	1
Water res. (powder)	1
Acid res. (powder)	3

Coef. disp. form. (pwr ser.)	
A0	3.17452404E+00
A1	-1.32156517E-02
A2	-1.65919934E-04
A3	2.76472367E-02
A4	4.83338934E-04
A5	1.20380702E-05
A6	6.02649728E-07
A7	0.00000000E+00
A8	0.00000000E+00

Mechanical properties	
Knoop hardness	670 (7)
Abrasion hardness	64
Young's mod. [GPa]	119.6
Shear mod. [GPa]	46.1
Poisson's ratio	0.298
Stress optical coef. [1E-5 nm/cm/Pa]	1.43

Deviation of relative partial disp.	
ΔPdC	0.0018
ΔPgF	-0.0087

Specific gravity
4.57

Relative $\Delta n / \Delta T$ [1E-6/°C]																
Temp. [°C]	1.083	t	s	A'	r	C	C'	He-Ne	d	e	F	F'	g	h	0.389	
80 to 90 (ref.)	3.5	3.6	3.8	4.0	4.1	4.3	4.4	4.4	4.7	5.0	5.6	5.6	6.3	6.9	7.4	
60 to 80 (ref.)	3.4	3.5	3.7	3.9	4.0	4.2	4.2	4.3	4.5	4.8	5.4	5.5	6.1	6.8	7.3	
40 to 60	3.3	3.4	3.6	3.7	3.9	4.1	4.1	4.2	4.4	4.7	5.3	5.3	5.9	6.6	7.0	
20 to 40	3.2	3.3	3.5	3.7	3.8	4.0	4.0	4.1	4.3	4.6	5.1	5.2	5.8	6.4	6.8	
0 to 20	3.2	3.3	3.5	3.6	3.7	3.9	3.9	4.0	4.2	4.5	5.0	5.1	5.7	6.2	6.7	
-20 to 0	3.2	3.3	3.5	3.6	3.7	3.9	3.9	4.0	4.2	4.5	5.0	5.1	5.6	6.2	6.6	
-40 to -20	3.3	3.4	3.6	3.7	3.8	4.0	4.0	4.1	4.3	4.5	5.0	5.1	5.6	6.2	6.6	
-60 to -40 (ref.)	3.5	3.6	3.8	3.9	4.0	4.1	4.2	4.2	4.4	4.7	5.2	5.2	5.7	6.3	6.7	
-70 to -60 (ref.)	3.7	3.8	4.0	4.1	4.2	4.4	4.4	4.4	4.6	4.9	5.4	5.4	5.9	6.4	6.8	

Absolute $\Delta n / \Delta T$ [1E-6/°C]																
Temp. [°C]	1.083	t	s	A'	r	C	C'	He-Ne	d	e	F	F'	g	h	0.389	
80 to 90	2.4	2.5	2.7	2.9	3.0	3.2	3.2	3.3	3.5	3.8	4.4	4.5	5.1	5.8	6.3	
60 to 80	2.2	2.3	2.5	2.7	2.8	3.0	3.0	3.1	3.3	3.6	4.2	4.2	4.9	5.5	6.0	
40 to 60	1.9	2.0	2.2	2.4	2.5	2.7	2.7	2.8	3.0	3.3	3.9	3.9	4.5	5.1	5.6	
20 to 40	1.7	1.8	2.0	2.1	2.2	2.4	2.4	2.5	2.7	3.0	3.5	3.6	4.2	4.7	5.2	
0 to 20	1.4	1.5	1.7	1.8	2.0	2.1	2.2	2.2	2.4	2.7	3.2	3.3	3.8	4.4	4.8	
-20 to 0	1.2	1.2	1.4	1.6	1.7	1.8	1.9	1.9	2.1	2.4	2.9	2.9	3.5	4.0	4.4	
-40 to -20	0.9	1.0	1.2	1.3	1.4	1.5	1.6	1.6	1.8	2.1	2.5	2.6	3.1	3.6	4.0	
-60 to -40	0.6	0.7	0.9	1.0	1.1	1.2	1.3	1.3	1.5	1.8	2.2	2.3	2.7	3.2	3.6	
-70 to -60	0.4	0.5	0.7	0.8	0.9	1.0	1.1	1.1	1.3	1.5	2.0	2.0	2.5	3.0	3.3	

Coef. disp. form. (frac. eq.) (ref.)	
P1	1.10686191E-01
Q1	7.43053260E+01
P2	2.71367682E-02
Q2	3.09494207E-02
P3	3.93128419E-01
Q3	5.72630320E-03

Fitting error of disp. form. σ [1E-6]		
	Visible	Infrared
Power ser. eq.	0.8	3.9
Frac. eq. (ref.)	0.9	4.0

Prod. Freq. (A to D)	A
----------------------	---

Similar glass type			
OHARA	S-LAH65VS	HOYA	TAF3
CDGM	H-ZLaF50E	SCHOTT	N-LASF44

2022-7-1	StP, AP, SP
2020-4-1	Similar glass type
2019-4-1	Transmittance